

ABS 66Y SOLVENT CEMENT

ABS 66Y Premium Grade - Yellow

PRODUCT DESCRIPTION

ABS 66Y (Premium Grade) is a medium bodied premium grade cement for all ABS pipe systems. Very fast setting for professional use. CSA certified for Drain, Waste & Vent (DWV) sewer pipe and fittings. Meets ASTM D-2235 requirements. Recommended for pipe up to 6" (152 mm) in diameter. Used with our approved CLEANER 33.



DIRECTIONS FOR USE

Applying the Cement will require the use of CLEANER 33 and following the step-by-step procedure for cutting the pipe and preparing the surfaces. These procedures are set out in detail on the Cement and Primer container labels.

PACKAGING

The ABS 66Y Solvent Cement is packaged in a variety of metal container sizes and types, which include the screw top cans with an applicator dauber attached.

SAFETY DATA

It is extremely important to read the relevant safety data in the WHMIS section of the label and the relevant Material Safety Data Sheet, before using the product.

TYPICAL PROPERTIES

| | |
|-------------------|---|
| APPEARANCE: | Yellow liquid |
| VISCOSITY RANGE: | 600-700 cps @ 23°C |
| FLAMMABILITY: | Extremely flammable |
| ODOUR: | Strong Ketone Odour. Use in well-ventilated areas |
| SOLVENT: | Methyl Ethyl Ketone (MEK) |
| SPECIFIC GRAVITY: | 0.86 to 0.90 |
| FREEZING POINT: | <0°C |
| SHELF LIFE: | Approx. eighteen months stored in tightly closed containers at room temperature |
| FLASH POINT: | - 4°C TAG Closed Cup |

| | | |
|--------------|----------------|----------------|
| SET UP TIME: | -1° C to 10° C | 4 – 5 minutes |
| | 10° C to 21° C | 2 – 3 minutes |
| | 21° C to 32° C | 0.5 – 1 minute |

VOC INFORMATION: This product emits VOC's (volatile organic compounds) in its use. Always ensure that the use of this product complies with local VOC Emission Regulations, were they exist.

The VOC level is 600 grams/litre (SCAQMD Test Method 316A)